

PRODUCT DATA SHEET

POLYETHYLENE

Borstar® HE2630

NATURAL HDPE FOR NON-PRESSURE UTILITY PIPES

DESCRIPTION

HE2630 is a natural HDPE, designed for non-pressure pipes. It has a high density level giving excellent radial stiffness. It is easy to extrude through narrow die gap and the narrow molecular weight distribution makes it ideal for blowing and forming to e.g. thin-walled corrugated pipes.

HE2630 is a natural stabilized compound that can be given the desired color by addition of suitable color master batch. If weather resistance is needed, a UV stabilizer has to be added.

APPLICATIONS

HE2630 is recommended for:

Non pressure utility pipes

KEY FEATURES

HE2630 offers excellent balance of process-ability and mechanical properties

Property	Typical Value*	Test Method
Density	952kg/m	ASTM D 792
Melt Flow Rate (190°C/5.0kg)	0.37 g/10min	ASTM D1238

* Typical properties and data should not be used for specification work

PROCESSING CONDITIONS

The actual extrusion conditions will depend on the type of equipment used. They will also depend on size and wall thickness of the pipe produced. The following conditions may be used as a guideline when starting up the extruder:

Max. preheating temperature 90°C

Cylinder 180 – 210°C

Head 200 – 210°C

Die 200 – 210°C

Melt temperature 200 – 210°C

Specific recommendations for processing conditions can be determined only when the applications and type of equipment are known. Please contact your local Borouge representative for such particulars.

STORAGE

HE2630 should be stored in dry conditions at temperature below 60°C and protected from UV-light.

Improper storage can initiate degradation, which results in odor generation and can have negative effects on physical properties of this product.

More information on storage can be found in Safety Information Sheet (SIS) for this product.

SAFETY

HE2630 is not classified as dangerous preparation.

Dust and fines from the product may give a risk for dust explosion. All equipment should be properly earthed. Inhalation of dust may irritate the respiratory system and should be avoided. During processing of the product small amounts of fumes are generated, which require proper ventilation.

RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Information Sheet

Statement on chemicals, regulations and standards

STANDARDS

Borouge is certified to various ISO standards, please refer to Borouge.com for more information.

DISCLAIMER

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however, we do not assume any liability whatsoever for the accuracy and completeness of such information. Borouge makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of Borouge's products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Borstar® is a trademark of the Borealis group